

TECHNICAL DATA SHEET

Use	is a material for the FDM (FFF) 3D printing additive technology		
Material	Acrylonitril styren acrylate, Petroleum product		
Diameter	1,75 mm		
Tolerance	± 0,05 mm		
Weight	0,75 kg netto ± 5 % / 0,9 kg brutto ± 5 %		
Packing	Spool in Vacuum ZIP bag, inserting to paper box, all in LDPE foil.		
Colours	See www.filament-pm.com		
Solvents	Aceton		
Printing Properties			
Temperature HE	240 - 260°C		
Temperature HB	100 - 110 °C		
Surface bed	Kapton, Ultem, PET foil, commons for FDM printing		
Cooling print object	Max 30%		
Nozzle	All diameters		
Printer space	Open / Close		
Material Properties			
Thermal	Vicat softening temperature	ISO 306	96 °C
	Heat deflection temperature	ISO 75	87 °C
Mechanical	Impact strength	ISO 179	12 kJ/m²
	Flexural modulus	ISO 178	1800 MPa
Physical	Density	ISO 1183/B	1,07 g/cm³
	Melt Flow Index	ISO 1133	20 g/10 min