

TECHNICAL DATA SHEET FOR PRODUCT:

PLA+ FILAMENT

Use	is a material for the FDM (FFF) 3D printing additive technology		
Material	polylactid acid ,biodegradabilic material, non petroleum product		
Diameters	1,75 mm		
Tolerance	± 0,05 mm		
Weight	1,0 kg netto ± 5% / 1,3 kg brutto ± 5%		
Packing	spool in Vacuum ZIP bag, inserting to paper box, all in LDPE foil		
Colours	views on web https://shop.filament-pm.com/PLA%2B		
Solvents	1,2 Dichloroethane, Toluene, Tetrahydrofuran,		
Printing Properties:			
Temperature HE	Ø1,75: 190 – 210 °C		
Temperature HB	60 °C		
Surface bed	kapton, ultem, PET foil, commons for FDM printing		
Cooling print object	YES		
Nozzle	All diameters		
Printer space	Open / Close		
Material Properties:			
Thermal	vicat softening temperature	ISO 306	55 °C
	heat deflection temperature	ISO 75	55 °C
Mechanical	impact strength	ISO 179	16.5 kJ/m²
	flexural modulus	ISO 178	3000 MPa
Physical	Density	ISO 1183/B	1,25 g/cm³
	Melt Flow Index	ISO 1133	3 g/10 min