

Technical data sheet

SILK

Use	It is a material for the FDM (FFF) 3D printing additive technology.
Material	SILK
Diameter	1,75 mm
Tolerance	± 0,05 mm
Weight	1,0 kg netto ± 5 % / 1,3 kg brutto ± 5 %
Packing	Spool in Vacuum ZIP bag, inserting to paper box, all in LDPE foil.
Colour	See www.filament-pm.com
Solvents	1,2 Dichloroethane

Printing Properties	
Temperature HE	210 – 250 °C
Temperature HB	60 °C
Surface bed	Kapton, Ultem, PET foil, commons for FDM printing
Cooling print object	Yes
Nozzle	All diameters
Printer space	Open / Close

Material Properties			
Thermal	Vicat softening temperature	IISO 306	65 °C
	Heat deflection temperature	ISO 75	56 °C
Mechanical	Impact strength	ISO 179	19 kJ/m ²
	Flexural modulus	ISO 178	3 000 MPa
Physical	Density	ISO 1183/B	1,24 g/cm ³
	Melt Flow Index	ISO 1133	6,6 g/10 min



Filament PM

Haňovice 18, 783 21 Czech republic

IČ: 00147346

tel. +420 585 100 308

e-mail: info@filament-pm.com

www.filament-pm.com

Filament